

Standard	ACN (%)	Viscosity Mooney ML (1+4) 100°C
EUOPRENE N 2845	28	45
EUOPRENE N 2860	28	60
EUOPRENE N 3330	33	30
EUOPRENE N 3345	33	45
EUOPRENE N 3360	33	60
EUOPRENE N 3380	33	80
EUOPRENE N 3945	39	45
EUOPRENE N 3960	39	60
EUOPRENE N 3980	39	80
EUOPRENE N 4560	45	60

Green	ACN (%)	Viscosity Mooney ML (1+4) 100°C
EUOPRENE N 1934 GRN	19	45
EUOPRENE N 2830 GRN	28	30
EUOPRENE N 2845 GRN	28	45
EUOPRENE N 2860 GRN	28	60
EUOPRENE N 3330 GRN	33	30
EUOPRENE N 3345 GRN	33	45
EUOPRENE N 3380 GRN	33	80
EUOPRENE N 3945 GRN	39	45

NBR-PVC	ACN (%)	Viscosity Mooney ML (1+4) 100°C
EUOPRENE N OZO 7028	19,5	75

NBR-PVC	ACN (%)	Viscosity Mooney ML (1+4) 100°C
EUOPRENE N OZO 7028/60	19,5	60
EUOPRENE N OZO 7033	23	75
EUOPRENE N OZO 7033/60	23	60
EUOPRENE N OZO 7039	27	75
EUOPRENE N OZO 7045	31,5	95
EUOPRENE N OZO 5033	16,5	70