

## LUVOMAXX® BC "Low-Grit" Grades

	<b>ASTM Test method</b>	<b>N-550 LG</b>	<b>N-650 LG</b>
<b>Oil adsorption (ml/100g)</b>	D 2414	121	122
<b>Iodine no. (mg/g)</b>	D 1510	43	36
<b>Ash (% max.)</b>	D 1506	0.5	0.5
<b>Sieve residue 325 mesh (ppm max.)</b>	D 1514	20	20
<b>Nitrogen surface area (m<sup>2</sup>/g)</b>	D 6556	40	36
<b>Appearance</b>	-	black pellets	black pellets