

<b>High Cis</b>	<b>Cis (%)</b>	<b>Viscosity ML (1+4) 100°C</b>
NEOCIS BR 40	98	43
NEOCIS BR 60	98	63
<b>Low Cis</b>	<b>Cis (%)</b>	<b>Viscosity ML (1+4) 100°C</b>
INTENE 50	38	48
<b>High Vinyl</b>	<b>Vinyl (%)</b>	<b>Viscosity ML (1+4) 100°C</b>
EUOPRENE BR HV80	80	70