

<b>Solution Styrene Butadiene Rubber (SSBR)</b>	<b>Grade</b>	<b>Styrene (%)</b>	<b>Vinyl (%)</b>	<b>Viscosity ML (1+4) 100°C</b>	<b>Oil Content phr</b>
S-SBR	SOL 1205	25		53	-
S-SBR	SOL R72606	25	67	45	37,5 DAE
S-SBR	SOL R72612	25	67	48	36,8 MES
S-SBR	SOL R72613	25	64	60	-
S-SBR	SOL 72614	25	64	55	37,5 TDAE
S-SBR	SOL R2525	26	24	52	-