

## Dead Burned Magnesite - DBM

### Typical chemical values

Product	MgO (%)	SiO <sub>2</sub> (%)	CaO (%)	Al <sub>2</sub> O <sub>3</sub> (%)	Fe <sub>2</sub> O <sub>3</sub> (%)	Loss on ignition(%)	Particle size
<b>Dead burned magnesite 9003</b>	90,00	4,50	2,50	1,50	1,50	1,00	0 - 3 mm (< 1 mm: 55,00%)
<b>Dead burned magnesite 9010</b>	90,00	4,50	2,50	1,50	1,50	0,60	0 - 10 mm (< 1 mm: 10,00%)
<b>Magnesium oxide TA-3</b>	91,50	3,2	1,85	1,00	1,25	0,95	60,00% < 63 μm/ 250 mesh
<b>Magnesium oxide TA-6</b>	89,50	7,00	3,50	0,50	0,50	0,50	60,00% < 63 μm/ 250 mesh
<b>Dead burned magnesite Extra</b>	96,50	1,00	2,00	0,10	0,60	0,20	0 - 15 mm (< 1 mm: 10,00%)