

Product	Appearance	Properties and applications	Chlorine content (%)	Mooney ML (1+4) @ 125°C
CPE 6035	white powder	high molecular weight, for applications with requirements on mechanical properties	34 – 36	80 – 105
CPE 6135	white powder	medium molecular weight, mainly for cable applications	34 – 36	65 – 72
CPE 6235	white powder	medium molecular weight, suitable for good surface quality and high extrusion speed, hoses and cables	34 – 36	70 – 80
CPE 6335	white powder	lower molecular weight, easy processing, for applications without high requirements on mechanical properties	34 – 36	45 – 65
CPE 6140	white powder	especially suitable for applications that require high oil- and flame resistance, e.g. mining cables	39 – 41	70 – 90
CPE 6240	white powder	easy processing and good compatibility with other materials	39 – 41	50 – 80
CPE 4135	white powder	suitable for high mechanical requirements	34 – 36	85 – 100