

Phenol-formaldehyde resins

| Product | Appearance | Active ingredient | Softening point (°C) | Application |
|--------------------------|----------------|---|----------------------|--------------------------|
| ALNOVOL® PN 160 | Brown granules | Alkyl modified phenol-formaldehyde resin | 101 - 113 | Reinforcement |
| ALNOVOL® PN 320 | Brown granules | Non-modified phenol-formaldehyde resin | 108 - 120 | Reinforcement |
| ALNOVOL® PN 760 | Brown granules | Modified phenol-formaldehyde resin system | 93 - 106 | Rubber to metal adhesion |
| ALNOVOL® VPN 1132 | Brown granules | Specific modified phenol-formaldehyde resin | 115 - 145 | Reinforcement |