

Product	Appearance	Properties and applications	Chlorine content (%)	Shore hardness A
CPE 3135	white powder	pipes, profiles, sheets made of rigid PVC and other polymers	34 - 36	< 65
CPE 7130	white powder	especially for magnetic applications, for high dosage levels of magnetic powders	29 - 31	< 70
CPE 5236	white powder	suited for TPE and soft PVC, good surface quality	35 - 37	< 60
CPE 2135	white powder	especially for flame retardant ABS	34 - 36	< 75