

Solution Styrene Butadiene Rubber (SSBR)	Grade	Styrene (%)	Vinyl (%)	Viscosity ML (1+4) 100°C	Oil Content phr
S-SBR	SOL 1205	25		53	-
S-SBR	SOL R72606	25	67	45	37,5 DAE
S-SBR	SOL R72612	25	67	48	36,8 MES
S-SBR	SOL R72613	25	64	60	-
S-SBR	SOL 72614	25	64	55	37,5 TDAE
S-SBR	SOL R2525	26	24	52	-