

Emulsion Styrene Butadiene Rubber (SBR)	Grade	Styrene (%)	Viscosity ML (1+4) 100°C	Oil Content phr
E-SBR	1500	23,5	52	-
E-SBR	1502	23,5	52	-
E-SBR	1502 F	23,5	52	-
E-SBR	1509	23,5	33	-
E-SBR	1721	40	54	37,5 DAE
E-SBR	1723	23,5	48	37,5 TDAE
E-SBR	1739	40	52	37,5 TDAE
E-SBR	1778	23,5	49	37,5 NAPH
HSR	HS 630	63	56	-