

| Product | Form | Application | Benefits | D50 sedigraph | D98 sedigraph | Brightness [GEB] |
|-------------------------------------|--------------------------------------|--|--|---------------|---------------|------------------|
| SILVERLINE® 002 | Natural white powder, bags | Dusting, release agent talc | Excellent partitioning low cost agents | 8,4 | 55 | 75 |
| VERTAL® 92 | Natural white powder, bags | Dusting | Powdering, cable layer insulation | 17,5 | 45 | Y72 |
| VERTAL® 97 | Natural white powder, bags | Dusting | Powdering, cable layer insulation | 2,2 | 31 | 86 |
| MISTRON® VAPOR R (powder) | Natural white powder, bags | Non-black compounds, EPDM roofing, MRG, hoses, weather stripping | Processability, reinforcement, durability and toughness | 2,2 | 31 | 86 |
| MISTRON® VAPOR R (compacted) | White powder compacted, bags | Non-black compounds, EPDM roofing, MRG, hoses, weather stripping | Processability, reinforcement, durability and toughness | 2,2 | 31 | 86 |
| MISTRON® VAPOR RE | Natural white powder, bags | Black compounds, window seals, MRG | Processability, reinforcement, durability and toughness | 2,2 | 31 | 80 |
| MISTRON® VAPOR ULTRA | Natural white powder very fine, bags | Black compounds, window seals, MRG | Processability, reinforcement, durability and toughness. Improve extrudate surface quality, enhanced elongation at break | 2 | 12 | 88 |
| MISTRON® CB* | Surface treated powder, bags | Medical stopper, MRG, hoses, seals and gaskets, printed circuit boards | High modulus and good compression set | 2,2 | 31 | 86 |

| Product | Form | Application | Benefits | D50 sedigraph | D98 sedigraph | Brightness [GEB] |
|-----------------------------------|---|--|---|---------------|---------------|------------------|
| MISTRON® CB6* | Surface treated and finer and densified, bags | Medical stopper, MRG, hoses, seals and gaskets, printed circuit boards | High modulus and good compression set | 2 | 25 | 88 |
| MISTRON® HYPERPLATE™ | Delaminated talc, extreme lamellar, bags | Tire inner liners automotive, fuel and hydraulic hoses | Superior permeability resistance, flex fatigue, long life, fire retardancy | 1,2 | 8 | 80 |
| MISTRON® HYPERPLATE™ ULTRA | Delaminated talc, extreme lamellar, bags | Tire inner liners automotive, fuel and hydraulic hoses | Superior permeability resistance, flex fatigue, long life, fire retardancy | 1,5 | 10 | 83 |
| MISTROFOAM®* | Surface treated, bags | Wire and cable insulation, MRG, hoses, seals, foamed polymer products | High modulus and good compression set, Improved water resistance and electrical properties in wire and cable | 2,2 | 31 | 82 |
| MISTRON® ZSC* | Surface treated, bags | Wire and cable insulation, MRG, hoses, seals, gaskets | High modulus and good compression set, Improved water resistance, higher dielectrical strengths, properties in wire and cable | 2 | 25 | 87 |
| MISTRON® TZ2* | Surface treated, bags | Wire and cable insulation, MRG, hoses, seals, gaskets | High modulus and good compression set, Improved water resistance and electrical properties in wire and cable | 2 | 25 | 87 |

| Product | Form | Application | Benefits | D50 sedigraph | D98 sedigraph | Brightness [GEB] |
|---------------------|-----------------------|---|--|---------------|---------------|------------------|
| MISTROPHOBE* | Surface treated, bags | Wire and cable insulation, MRG, hoses, seals, gaskets | High modulus and good compression set, reaktive chemistry with any unsaturated cure system, that enhances hydrophobicity, wet electrical performance and mechanical properties | 2 | 25 | 88 |

* = surface treated