

LUVOMAXX® BC Carcass Grades

	ASTM Test method	N-539	N-550	N-650	N-660	N-772
Oil adsorption (ml/100g)	D 2414	111	121	122	90	65
Iodine no. (mg/g)	D 1510	43	43	36	36	30
Ash (% max.)	D 1506	0.5	0.5	0.5	0.5	0.5
Sieve residue 325 mesh (ppm max.)	D 1514	100	200	250	250	500
Nitrogen surface area (m²/g)	D 6556	38	40	36	35	32
Appearance	-	black pellets	black pellets	black pellets	black pellets	black pellets