

LUVOMAXX® BC Tread Grades

| | ASTM Test method | N-115 | N-121 | N-134 | N-220 | N-234 |
|--|-----------------------------|------------------|------------------|------------------|------------------|------------------|
| Oil adsorption (ml/100g) | D 2414 | 113 | 131 | 127 | 114 | 125 |
| Iodine no. (mg/g) | D 1510 | 160 | 121 | 142 | 121 | 120 |
| Ash (% max.) | D 1506 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 |
| Sieve residue 325 mesh (ppm max.) | D 1514 | 500 | 250 | 250 | 250 | 200 |
| Nitrogen surface area (m²/g) | D 6556 | 137 | 122 | 143 | 119 | 119 |
| Appearance | - | black pellets | black pellets | black pellets | black pellets | black pellets |