

| Emulsion Styrene Butadiene Rubber (SBR) | Grade | Styrene (%) | Viscosity ML (1+4) 100°C | Oil Content phr |
|--|--------------|--------------------|---|----------------------------|
| E-SBR | 1500 | 23,5 | 52 | - |
| E-SBR | 1502 | 23,5 | 52 | - |
| E-SBR | 1502 F | 23,5 | 52 | - |
| E-SBR | 1509 | 23,5 | 33 | - |
| E-SBR | 1721 | 40 | 54 | 37,5 DAE |
| E-SBR | 1723 | 23,5 | 48 | 37,5 TDAE |
| E-SBR | 1739 | 40 | 52 | 37,5 TDAE |
| E-SBR | 1778 | 23,5 | 49 | 37,5 NAPH |
| HSR | HS 630 | 63 | 56 | - |